

Chosen material:



Balsa-wood
same material?

勝特力材料 886-3-5753170
勝特力电子(上海) 86-21-54151736
勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

MODEL BALSA

Product description

Adhesive for wooden models.



Where to use

Balsa-wood, astralon, celluloid, paper and textile. Especially suitable for model making.

Properties

- Dilutability: do not dilute.
- Temp. resistance: up to + 100° C.
- Frost resistance: good.
- Resistance to moisture: good.
- Resistance to chemicals: resistant to diluted acids and petrol.

勝特力材料 886-3-5753170
勝特力电子(上海) 86-21-54151736
勝特力电子(深圳) 86-755-83298787
Http://www.100y.com.tw

MODEL BALSA

PRODUCT DESCRIPTION

Adhesive for wooden models.

FIELD OF APPLICATION

Balsa-wood, astralon, celluloid, paper and textile. Especially suitable for model making.

PROPERTIES

Dilutability: do not dilute.

Temp. resistance: up to + 100° C.

Frost resistance: good.

Resistance to moisture: good.

Resistance to chemicals: resistant to diluted acids and petrol.

TECHNICAL DATA

Basic material : nitrocellulose.

Colour : transparant.

Solids content : 40 %.

Specific gravity : 1070 kg/m3.

Viscosity : 4 Pa.s. at + 20° C.

Flash point : + 5° C.

APPLICATION

Surface treatment: The materials to be bonded must be properly dry, clean and free from dust.

Application temp.: Minimal + 5° C.

Directions for use: Apply a thin coat of adhesive to both parts and leave to dry for 1-2 minutes. Next apply another coat to one of the surfaces and bring the parts immediately together. In the case of angular bonds apply a thick coat of Bison-Balsa to the angle.

STAINS

Remove adhesive stains with acetone.

STORAGE PROPERTIES

The shelf life is about 2 years, provided it is stored in un-opened packing in a cool place.

WARNING

Symbol = F.

R 11 = Highly flammable.

S 2 = Keep out of reach of children.

S 16 = Keep away from sources of ignition – No smoking.

S 46 = If swallowed, seek medical advice immediately and show this container or label

S 51 = Use only in well ventilated areas.



TRANSPORT CLASSIFICATIONS

On land : RID/ADR = 3-4b.

At sea : IMO = 3.2.

Our instructions are based on extensive investigations and experience. In view of the large variety of materials and the conditions under which our products are applied, no responsibility can be assumed for the results obtained and/or any damage caused from the use of the product. However, our Service Department is quite willing to supply any advice needed.

Head office: Bison International - P.O. Box 160, 4460 AD Goes (NL). Tel. 31-113-248248, Fax 31-113-232077, e-mail: info@bison.boltongroup.nl