

Technical Data Sheet

勝特力材料 886-3-5753170
勝特力电子(上海) 86-21-54151736
勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

PRODUCT DESCRIPTION:	Silicone Heat Transfer Compound	DATE:	03/97
PRODUCT CODE:	HTS	PAGES:	1

PRODUCT DESCRIPTION

Silicone Heat Transfer Compound is a metal oxide filled silicone oil providing an extremely efficient and exceptionally thermally conductive compound which will operate over a wide temperature range. Electrolube Heat Transfer Compound is recommended where the efficient and reliable thermal coupling of electrical and electronic components is required or between any surface where thermal conductivity of heat dissipation is important.

A full range of heat transfer products are available from Electrolube. This range includes non-silicone based pastes (HTC), a RTV rubber (TCR), an adhesive epoxy (TBS) and an epoxy based potting resin (ER2074). A even higher thermally conductive paste is also available, order code HTSP, for special applications where thermal management is critical.

FEATURES

- * Excellent non-creep characteristics.
- * Wide operating temperature range with low evaporation weight loss.
- * Excellent thermal conductivity even at high temperatures.
- * Easy to handle, economic in use and low in toxicity.

APPLICATION

Apply to the base and mounting studs of diodes, transistors, thyristors, heat sinks, silicone rectifiers and semi-conductors, thermostats, power resistors and radiators.

PROPERTIES

Colour:	White
Base:	Silicone Oil
Thermo-conductive Components:	Powdered Metal Oxides
Density @ 20°C:	2.10 g/cm ³
Temperature Range:	-100°C to +200°C
Thermal Conductivity:	0.9 W/mK
Weight Loss after 96 hours @ 100°C:	0.84%
Permittivity @ 10 ⁶ Hz:	4.9
Specific Resistance:	1 x 10 ¹⁵ Ohms/cm
Dielectric Strength:	18 kV/mm
Penetration:	220-270

PACKAGING

20 ml Syringe
35 ml Luer Lock Syringe
1 Kg Bulk

ORDER CODE

HTS20S
HTS35SL
HTS01K

Copyright Electrolube 1997

All information is given in good faith but without warranty. Properties are given as a guide only and should not be taken as a specification. Electrolube cannot be held responsible for the performance of its products within any application determined by the customer, who must satisfy themselves as to the suitability of the product.