



勝特力科技有限公司

www.100y.com.tw

Heatproof Tape

耐熱膠帶

勝特力材料 886-3-5753170
勝特力电子(上海) 86-21-54151736
勝特力电子(深圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)



厚度	0.18mm
尺寸	20mm*30M 25mm*30M
耐熱	180°C
用途	適用於冶金、建築材料以及鑄造等工作部門，用以 180°C 以下物料，耐熱性好的合成橡膠，使用壽命長，膠帶表面光滑平整。



69 Electrical Tape - OEM

Glass Cloth With Silicone Pressure Sensitive Adhesive

Data Sheet

勝 特 力 材 料 886-3-5753170
勝 特 力 電 子 (上 海) 86-21-34970699
勝 特 力 電 子 (深 圳) 86-755-83298787
[Http://www.100y.com.tw](http://www.100y.com.tw)

1. Product Description

3M™ 69 Glass Cloth Electrical Tape is a white glass cloth tape with a high-temperature thermosetting silicone adhesive. The thermosetting adhesive provides an increased bond once applied in areas of high ambient temperatures. 69 Tape is UL recognized for continuous use up to 200°C. It conforms to Military Specification No. MIL-I-19166C.

2. Applications

- Insulating electric and induction type furnace power supply leads
- Securing high temperature, non-PSA insulations (such as asbestos and glass) in high temperature areas
- Securing Scotch 77 Fire Retardant Electric Arc Proofing Tape
- Replacing 3M 27 Glass Cloth Electrical Tape in locations where a higher-temperature tape is needed
- Reinsulating and repairing coils on mining machines
- Reinforcing insulation in electrical installations where heavy loads cause high heat and breakdown of original insulation (e.g. motor control exciter feeds)

- Splicing silicone-covered glass wire where splices require more abrasion resistance and mechanical strength than can be provided by silicone tapes
- Insulating Class "H" dry-type transformer leads

Typical Properties

Property	Value*
Thickness ¹	7.0 mils (.177 mm)
Tensile Strength ¹	180 lbs./in (314 N/10mm)
Elongation at Break ¹	5%
Adhesion ¹	40 oz/in (4.4 N/10mm)
Electrical Strength ¹	3000V
Insulation Resistance ¹	4.8 x 10 ⁴ megohms
Electrolytic Corrosion Factor ²	0.9
Functional for Life of Component	200°C

* Not recommended for specification purposes. Product specifications will be provided upon request.

Test Methods:
¹ASTM-D-1000
²3M Test Method